










1. Size & Packing

Size(mm)	Thickness(mm)	Pcs/Box	m ² /Box	Kg/m ²
500x500	3	16 pcs/box	4m ²	5.0
	5	10 pcs/box	2.5m ²	8.2
1000x500	3	8 pcs/box	4m ²	5.0
	5	5 pcs/box	2.5m ²	8.2

2. Test Result

Test Item		Standard	Technical data
Level of use		EN 685	33
Fraying		EN 1814	Frayproof
Thermal resistance		ISO 8302	0.02m ² K/W
Castor chair resistance		EN 985	No damage
Dimensional stability		ISO 23999 / EN 434	≤ 0.10% (Norm: ≤ 0.25%)
		EN 986	Passed
Fire resistance		EN 13501	Bfl -s1
Formaldehyde group		EN 717-1	E1
Indoor air quality			Low VOC
Underfloor heating		EN 12524	Suitable
Light fastness		ISO 105-B02	≥ 6
Slip resistance		DIN 51130	R10
		EN 13893	DS
Flexibility		ISO 24344	Passed
Impact sound insulation		ISO 10140-3	9dB
Body Voltage		EN 1815	< 2kV
Squareness & Straightness		ISO 24342	No deviation
		ASTM F2055	≤ 0.01 in
Residual indentation		EN 433	≤ 0.1mm
		ASTM F1914	< 8%
Resistance to chemicals		ISO 26987	No Defects
		ASTM F925	No Defects